

6165 W Detroit St. • Chandler AZ 85226
+1 (602) 276-0406 • +1 (800) 528-8242 • FAX +1 (480) 961-0513
www.crafco.com

READ BEFORE USING THIS PRODUCT

GENERAL

Crafco RoadSaver 960 Gray Sealant is a gray colored, hot applied, single component, elastically modified composition of non-asphaltic ingredients and modifiers used to fill cracks and joints in asphalt and Portland cement concrete pavements. RoadSaver 960 Gray Sealant is supplied in powder/granular form in meltable bags which when melted and properly applied forms an adhesive and flexible compound that resists cracking in the winter and is resistant to flow at summer temperatures. RoadSaver 960 Gray Sealant is used in highway, street, and airfield pavements where the gray color is desired. VOC=0 g/l.

SPECIFICATION CONFORMANCE

Crafco RoadSaver 960 Gray Sealant meets all requirements of ASTM D6690 (AASHTO M324), Type I, "Joint and Crack Sealants, Hot-applied, for Concrete and Asphalt Pavements".

<u>Test</u>	<u>ASTM D6690, AASHTO M324 Type I Spec. Limits</u>
Cone Penetration at 77 °F (25 °C) (ASTM D5329)	90 units max
Softening Point (ASTM D36)	176 °F (80 °C) minimum
Bond, non-immersed, 0 °F (-18 °C), 50% ext.	Pass 5 cycles
Asphalt Compatibility (ASTM D5329)	Pass
Maximum Heating Temperature	400 °F (204 °C)
Minimum Application Temperature	380 °F (193 °C)

INSTALLATION

The unit weight of Crafco RoadSaver 960 Gray Sealant is 11.3 lbs. per gallon (1.35 kg/L) at 60 °F (15.5 °C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. RoadSaver 960 Gray Sealant can only be reheated one time after initial heating and shall not be maintained at maximum heating temperature for more than 8 hours. These instructions are provided with each pallet of product.

PACKAGING

Product is supplied in meltable bags each containing 35 +/- 2 lbs. (15.8 +/- 1 kg) of product with 60 bags per pallet. Bags are stacked and stretch wrapped on pallets containing approximately 2100 lbs. (953 kg). To use, the pallet wrap is removed, and individual bags are placed in Melter. There are no cardboard boxes or other components to open, empty, handle or dispose of. The bag melts into the product without affecting specification conformance.

WARRANTY

CRAFCO, Inc. warrants that CRAFCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafco shall not be responsible for improperly applied or misused products. Remedies against Crafco, Inc., as agreed to by Crafco, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafco, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafco, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafco recommendations for product installation**